

# AgC Silver Graphite

**SCOPE:** This information refers to silver graphite profiles and contact tips manufactured by blending of silver and graphite powder, compacting, sintering, extruding and rolling. The deformation results in the alignment of graphite particles along the direction of the extrusion and rolling. A brazeable silver side is produced by decarburization. Profiles clad with a brazing alloy and pre-soldered contact tips are available.

## Designation of standard compositions

Profiles show a parallel orientation of the graphite to the contact surface and can be produced with 2 to 4 weight percent graphite.

Contact tips with 2, 3, 4, 5 and 6 % are available either with a parallel orientation (AgC II) or with a perpendicular orientation of the graphite to the contact surface (AgC\_I\_).

## Characteristics


- » best anti-welding properties of all contact materials on make with C-contents of 3 % and higher
- » best protection against contact welding of closed contacts under short circuit currents
- » low erosion on make
- » low contact resistance
- » inferior arc migration properties

## Applications

- » circuit breakers (MCCB, ACB)
- » earth leakage breakers (RCCB)
- » miniature circuit breakers (MCB)


## Microstructure

The directional deformation of the material during the manufacturing process causes a strong displacement of the graphite particles into graphite layers.




**AgC3**

longitudinal section (parallel to the direction of extrusion)



**AgC3**

cross section




**AgC5**

cross section

## Physical Properties

MATERIAL	DENSITY [g/cm <sup>3</sup> ]	ELECTRICAL CONDUCTIVITY [m/(Ω·mm <sup>2</sup> )]
AgC2	9.4	49
AgC3	9.1	47
AgC4	8.8	44
AgC5	8.6	43
AgC6	8.4	42

## Weld Break Force





**USA**

**Attleboro**

Umicore Electrical Materials USA, Inc.  
527 Pleasant Street, Building 11  
Attleboro, MA 02703  
Phone: +1 508 838 2064  
Fax: +1 508 838 2062  
[Jay.Burnett@am.Umicore.com](mailto:Jay.Burnett@am.Umicore.com)

**Glens Falls**

Umicore Technical Materials North America Inc.  
9 Pruy'n's Island Drive  
Glens Falls, NY 12801  
Phone: +1 732 485 2256  
Fax: +1 518-792-3162  
[Kay.Solecki@am.umicore.com](mailto:Kay.Solecki@am.umicore.com)

[www.UmicoreElectricalMaterialsUSA.com](http://www.UmicoreElectricalMaterialsUSA.com)

The information and statements contained herein are provided free of charge and are for general information purposes only. They are believed to be accurate at the time of publication, but Umicore makes no representations or warranty of any kind with respect thereto, express or implied, about the completeness, accuracy, reliability, suitability or availability. Use or application of such information or statements is at the user's discretion, without any liability on the part of Umicore. Nothing herein shall be constructed as a license or recommendation to use. Umicore reserves the right to alter any product or service at its own discretion. All sales are subject to Umicore's General Terms and Conditions of Sale and Delivery